

F70 - Fluorosilicone

Compound F70 was specifically developed for consistent performance.

Features and Benefits


- Consistent quality
- Cost-Effective

Equipment Locations

- Chamber Lid Seals
- Valve Seals
- Window Seals

Recommended Dry Processes

- Ashing



Color Blue
Service Temperature Range: -65°C to 176°C

Typical Physical Properties

Color	Blue
Hardness, Shore A	70
Tensile Strength, PSI (MPa)	1080 (7.45)
Elongation	240%
Compression Set: 22 hrs @ 175°C	17%
Service Temperature Range, °C (°F)	-65 to 176°C (-85 to 350°)